



2X ULTRA COVER ULTRA MATT FINISH SPRAYS

DESCRIPTION AND USES

Rust-Oleum® 2x Ultra Cover Enamel Sprays are designed to provide twice the coverage on wood, metal, plastic, wicker and more. These sprays cover surfaces with less spray passes, allowing projects to be completed faster and easier. 2X Ultra Cover Enamel Sprays feature an any angle spray that allows you to spray in any direction, even upside down. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying. Not for use on galvanised metal.

TIP: Some plastics made of polyethylene such as plastic storage containers are manufactured in a way that may hinder maximum paint adhesion. Test paint in a hidden area first.

PRODUCTS

SKU	DESCRIPTION (340g)
331183	Matt Evening Navy
331184	Matt Perfect Grey
331186	Matt Golden Leaf
331188	Matt Nantucket Blue
331189	Matt Harvest Grape
334022	Matt Clear
357855	Matt White
357854	Matt Black
357852	Matt Deep Teal
357856	Matt Slate

PRODUCT APPLICATION

SURFACE PREPARATION

Remove all dirt, grease, oil, salt, and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. Special precautions should be taken during surface preparation of pre-1960 painted surfaces as they may contain harmful lead. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding.

PRIMING

Use of 2X Ultra Cover primer provides superior adhesion and hiding and is especially recommended for bare wood and metal.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 10-32°C, and humidity is below 65% to ensure proper drying. Do not use on objects that may exceed 93°C surface temperature. Do not apply to galvanised steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 25-40 cm from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart to avoid drips and runs.

Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 21-27°C and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat or clear coat within 1 hour or after 48 hours. Apply clear in 2-3 light coats a few minutes apart.

NOTE: On plastic maximum paint adhesion and durability is achieved in 5-7 days.

CLEANUP

When finished spraying, wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick pin or other object into the stem.



**2X ULTRA COVER
ULTRA MATT FINISH SPRAYS**

PHYSICAL PROPERTIES

		2X ULTRA COVER ULTRA MATT SPRAYS
Resin Type		Modified Alkyd
Pigment Type		Varies by colour
Solvents		Acetone, Naptha, Mineral Spirits, Xylene, N-butyl Acetate
MIR		Max 0.95
Fill Weight		340g
Recommended Dry Film Thickness (DFT) per Coat		25-50µ (1.0-2.0 mils)
Practical Coverage at Recommended DFT (assume 15% material loss)		0.56-0.93 m ² /can
Dry Times at (21-27°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 48 hours
Dry Heat Resistance		93°C (200°F)
Shelf Life		5 years
Flash Point		-104°C (-156°F)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.